

AMENDMENTS TO THE CLAIMS

The following listing of claims replaces all previous claims, and listings of claims, in the application.

1. (Currently amended) A laminated resin film comprising at least one polyvinyl butyral film and at least one fluorine resin film of a tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride ternary copolymer which are laminated, wherein the fluorine resin film is bonded to the adjacent polyvinyl butyral film using an adhesive to which a silane coupling agent is added.

2. (Previously presented) The laminated resin film according to claim 1, wherein the at least one polyvinyl butyral film has a total thickness of 0.3 mm to 2.5 mm and at least one fluoreine resin film each has a thickness of 0.05 mm to 2 mm.

3. (Previously presented) The laminated resin film according to claim 1, wherein at least one fluorine resin film comprises two fluorine resin films, each of which constitutes one of both sides of the laminated resin film.

4. (Previously presented) The laminated resin film according to claim 3, further comprising an adhesive layer formed on each surface of the two fluorine resin films.

5. (Previously presented) The laminated resin film according to claim 4, wherein the adhesive layer comprises an adhesive containing a silane coupling agent.

6. (Previously presented) The laminated resin film according to claim 1, wherein at least one polyvinyl butyral film comprises two polyvinyl butyral films each of which constitutes one of both sides of the laminated resin film.

7. (Previously presented) The laminated resin film according to claim 1, further comprising a fluorine resin film and a polyvinyl butyral film which are laminated.

8. (Canceled)

9. (Currently amended) A laminated glass comprising:

a laminated resin film comprising at least one polyvinyl butyral film and at least one fluorine resin film of a tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride ternary copolymer which are laminated, wherein the fluorine resin film is bonded to the adjacent polyvinyl butyral film using an adhesive to which a silane coupling agent is added; and
two glass plates respectively laminated on both sides of the laminated resin film.

10. (Previously presented) The laminated glass according to claim 9, wherein the two glass plates are made of soda-lime glass or borosilicate glass.

11-20. (Canceled)